

Extruded PP-C sheets have a very good resistance to chemicals as well as a high impact strength, especially in the low temperature range.

### Mechanical properties:

Yield stress	DIN EN ISO 527	24 MPa
Elongation at yield	DIN EN ISO 527	11%
Tensile strength at break	DIN EN ISO 527	25 MPa
Elongation at break	DIN EN ISO 527	650%
Modulus of elasticity	EN ISO 178	900 MPa
Impact strength 23°C / -30°C	DIN EN ISO 179/1eU	without break / >70 kJ/m <sup>2</sup>
Notched imp. strength 23°C / -30°C	DIN EN ISO 179/1eU	35 kJ/m <sup>2</sup> / 4 kJ/m <sup>2</sup>

### Thermal properties:

Vicat B	DIN EN ISO 306	151°C
Coefficient of thermal expansionf.	ISO 7991	15 10 <sup>-5</sup> /K
Thermal conductivity	ISO 8302	0.22 W/m*K

### Electrical properties:

Dielectric constant	IEC 250	2.3
Dielectric loss factor	IEC 250	10 <sup>-4</sup>
Contact resistance	DIN EN 61340-5-1	10 <sup>15</sup> Ohm
Surface resistivity	DIN EN 61340-5-1	10 <sup>13</sup> Ohm
Dielectric strength	VDE 0303	30-40 kV/mm

### Typical properties:

Density	DIN EN ISO1183	0.92 g/cm <sup>3</sup>
Temperature range		-20 to +110°C
Weather resistance		low

Options\*: smooth, textured, coloured according to RAL or NCS colour scale and as recycled quality.  
 \* not all materials are available from stock; for some, order quantities of >1,000 kg may be required

**Buy plastic sheets easy online in standard or custom size: [www.s-polytec.com](http://www.s-polytec.com)**

S-POLYTEC GmbH - plastic sheets, adhesives and sealants. Highest quality for professional use!  
 Jurgensstraße 5 | 47574 Goch | Germany | Tel.: 0049-2823-9763360 | E-mail: [info@s-polytec.de](mailto:info@s-polytec.de)

The figures shown are the data of the sheet manufacturers. Values may differ depending on the production batch. This data sheet is not a guarantee for exact compliance with the values!